



## COMPARISON CHART (ENGLISH)

Designation	EasyPrime	EasyFlex	Easy Guard	Ameron/Devoe Bar Rust 235	Jotun Balloxy	International KBA
DFT	3 mils	12 mils	12 mils	12 mils	12 mils	12 mils
Adhesion	1,700 PSI	1,090 PSI	1,980 PSI	717 PSI	795 PSI	1060 PSI
Elongation	>34%**	>34%**	33.5%	< 6%*	11.4%	29.8%
Reverse Impact	86 In-lbs	27 In-lbs	1 In-lbs	1 in-lbs	3 In-lbs	7 In-lbs
Direct Impact		44 In-lbs	20 In-lbs	7 In-lbs	21 In-lbs	35 In-lbs
Water Absorption	0.93%	3.36%	1.17%	2.07%	4.50%	5.02%
Water Vapor Transmission	.0026 Perm-In	.0031 Perm-In	.0051 Perm-In	.0050 Perm-In	.0031 Perm-In	.0028 Perm-In
Pencil Hardness	2B	2B	F	4B	4B	4B
2000 Hr Salt Fog	Pass	Pass	Pass			

The following table describes results after 30 day fresh water immersion @ 50°C.

Designation	Easy Flex	International KBA
Reverse Impact	14 Inch-lbs	1 Inch-lbs
Direct Impact	40 Inch-lbs	6 Inch-lbs
Elongation, Conical Mandrel	> 34% Elongation**	< 6% Elongation*

\*\*The samples exhibited no cracking at all, giving an elongation of greater than or equal to 34%.

\*The samples exhibited cracking over the full length of the panel, giving an elongation of less than or equal to 6%.